

Amendments to the Specification

Please amend paragraph [0029] on page 12 as follows:

[0029] In one preferred implementation, the etching solution comprises from 0.1% to 50% by weight water, more preferably from ~~0.11%~~ 0.1% to 15% by weight water, even more preferably from 0.1% to 5% by weight water, and still more preferably has from 0.1% to 1% by weight water. In one even more preferred implementation, the etching solution has from 0% to less than 0.1% by weight water.